

## Rigips VARIO Jointfiller



### Product Description

Jointfiller VARIO is a polymer-modified and fine gypsum filler for joints and connections of plasterboards, for use with or without joint tape, as well for Glasroc F Ridurit, Glasroc F Reflex, Rigiton, Rigidur and Rigidur H Plasterboards.

Components: fine gypsum, fillers and adhesion.

### Advantages

VARIO is for use with or without Rigips joint tape, low shrinkage and excellent sanding.

### Application

VARIO is for filling the joints and connections of Vario-edges with or without joint tape. For filling the overlapping joints of Glasroc F Ridurit and Glasroc F Reflex Plasterboards with Rigips fiberglass joint tape. For filling the Rigidur- and Rigidur H fiber plasterboards with the edge profiles SK (without reinforcement, to install the boards with ca. 5mm distance) and AK (with Rigidur- glass fibre tape). With timber-framework is always to be used a joint tape. For filling Rigiton boards with joints without joint tape. For filling cracks, holes and smoothing uneven backgrounds. Full covering of plasterboards till Q4.

### Site Conditions

Air-, material and background temperature have to be above +5°C. Assure that the substrate is clean and dry and free of moulding oil remainders.

### Handling

Add approximately 1,6-1,8 kg VARIO into 1 litre of clean water and leave to stand for around 3 minutes. Then mix either by hand or with an electric drill with mud paddle (low speed) till the mixture is lump-free. After the stirring process do not add further material. (lumps)

On plasterboard:

Q1: Fill the joints and remove excessive material from surface. Bed Rigips paper tape into the joint and cover it with additional material.

Q2: If necessary remove excessive material from joints. Once material set, cover the existing joint with additional material. This is necessary as long as any transitions exist. Once the material has dried, sand it if necessary.

Q3: Cover full surface by thin strength of coating and that followed remove material to close the pores.

Q4: Cover full surface with minimum 2 mm strength of coating.

A reinforcing material may not be used or to extend by adding water.

Non-permissible extend can increase the risk of cracks.

Do not mix with other materials. Clean only with clean water.

### Quality Standard

Q1 – Q4

### EN-Classification

CE 4B – EN 13963 – A1– NPD

### Product Data

<b>Mixing ratio</b>	app. 1,6-1,8 kg / 1 L water
<b>Working-time</b>	app. 45 min.
<b>Consumption</b>	<u>joint area:</u> app. 0,3 kg/m <sup>2</sup> /mm Surface: 0,9kg/m <sup>2</sup>
<b>Fire resistance</b>	A1
<b>Flexural- and tensile bond strength</b>	According to EN 13963
<b>Package-size</b>	5 kg / 12,5 kg / 25 kg
<b>Storage</b>	
Shelf life: Ensure stock rotation and use within 12 months of the marked date. Use unsealed bags within 3 months. Protect from freezing - store between +2°C and +30°C.	

For further information please contact:

Saint-Gobain Rigips Austria GesmbH  
Wiener Neustädter Straße 63  
A-2734 Puchberg / Schneeberg

Tel. +43 (0) 2636 / 2203-0  
Fax +43 (0) 2636 / 2206-625

[www.rigips.com](http://www.rigips.com)

Indoor



Application

Manual



Handling

app. 45 min



Working time

app.0,3 kg/m<sup>2</sup>



Consumption

Q1-Q4



Quality standard

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.